intertek
Total Quality. Assured.


Test Report

NUMBER : TSNH00340204

Applicant : SHANXI SANZO GLASSWORK CO.,LTD
Rm1801C, Time-Square, No.27,Chuangye Street,
Xiaodian District,Taiyuan , Shanxi, China.030006
Attn :Jimmy

Date : Apr 24, 2020

Photo



****

To be continued

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.

David Zhang
Senior Manager

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司
No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384
Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com

intertek
Total Quality. Assured.

Test Report

NUMBER : TSNH00340204

Sample Description:

One (1) submitted sample said to be

Item Name	: glass
Item No.	: 600018
Material.	: glass
Buyer	: Prision brewing co llc
Supplier	: SHANXI SANZO GLASSWORK CO.,LTD
Manufacturer	: SHANXI SANZO GLASSWORK CO.,LTD
Country of Destination	: America
Country of Origin	: China

****

Tests Conducted:

As requested by the applicant, for details refer to attached page(s).

****

Conclusion：

Tested Sample	Standard	Result
Submitted Sample	As client's requirement reference to U.S. F.D.A. Compliance Policy Guides 7117.06(2005) and 7117.07(2005) on leachable lead and cadmium for ceramic ware	Pass

****

To be continued

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.

David Zhang
Senior Manager

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司
No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384
Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com

intertek
Total Quality. Assured.

Test Report

NUMBER : TSNH00340204

Leachable Lead And Cadmium Content - Internal Surface

As per U.S. F.D.A. C.P.G. 7117.06(2005), 7117.07(2005) and A.O.A.C. official methods of analysis 18th edition (2005) method 973.32 by Inductively Coupled Argon Plasma Spectrometry analysis.

Tested Sample	Internal depth (mm)	Volume of leaching solution (mL)	Lead (mg/L)	Cadmium (mg/L)
(1-1)	133	450	<0.05	<0.03
(1-2)	133	450	<0.05	<0.03
(1-3)	133	450	<0.05	<0.03
(1-4)	133	450	<0.05	<0.03
(1-5)	133	450	<0.05	<0.03
(1-6)	133	450	<0.05	<0.03
		Limit : (small hollowware)	2.0	0.5

Remark ： < = Less Than

Date sample received：Apr 17, 2020
Testing period：Apr 17, 2020 To Apr 23, 2020

****

End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司

No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384

Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com