Total Quality. Assured.


Test Report

NUMBER : TSNH00379625

Applicant : SHANXI SANZO GLASSWORK CO.,LTD
Rm1801C, Time-Square, No.27,Chuangye Street,
Xiaodian District,Taiyuan , Shanxi, China. 030006
Attn :Amanda

Date : Jun 10, 2021

Photo



****

To be continued

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.

David Zhang
Senior Manager

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司

No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384

Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com

Total Quality. Assured.

Test Report

NUMBER : TSNH00379625

Sample Description:

One (1) submitted sample said to be

Item Name	: glass cup
Material	: high borosilicate glass
Buyer	: BEOMHO CO.,LTD
Vendor	:SEOUL BUND CO.,LTD
Supplier/Manufacturer	: Shanxi Sanzo Glasswork CO.,LTD
Country of Destination	: Korea
Country of Origin	: China

****

Tests Conducted:

As requested by the applicant, for details refer to attached page(s).

****

Conclusion：

Tested Sample	Standard	Result
Submitted Sample	Client's requirement with reference to U.S. F.D.A. C.P.G. Sec.545.400 (CPG 7117.06) and C.P.G. Sec. 545.450 (CPG 7117.07) on leachable lead and cadmium for ceramic ware	Pass

****

To be continued

Authorized By :
For Intertek Testing Services
(Tianjin) Ltd.

David Zhang
Senior Manager

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司

No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384

Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com

intertek
Total Quality. Assured.

Test Report

NUMBER : TSNH00379625

Leachable Lead And Cadmium Content - Internal Surface

As per U.S. F.D.A. C.P.G. Sec.545.400 (CPG 7117.06),and C.P.G. Sec. 545.450 (CPG 7117.07) and A.O.A.C. official methods of analysis 18th edition (2005) method 973.32 by Inductively Coupled Argon Plasma Spectrometry analysis.

Tested Sample	Internal depth	Volume of leaching solution	Lead	Cadmium
	(mm)	(mL)	(mg/L)	(mg/L)
(1-1)	126	520	<0.05	<0.03
(1-2)	126	520	<0.05	<0.03
(1-3)	126	520	<0.05	<0.03
(1-4)	126	520	<0.05	<0.03
(1-5)	126	520	<0.05	<0.03
		Limit : (small hollowware)	2.0	0.5

Remark ： < = Less Than

Date sample received: Jun 04, 2021
Testing period: Jun 04, 2021 to Jun 09, 2021

****

End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

Intertek Testing Service (Tianjin) Ltd.
天祥(天津)质量技术服务有限公司

No. 7 Guiyuan Road, Huayuan Hi-Tech Park, Tianjin, 300384 China
天津华苑新技术产业园区桂苑路7号
邮编 300384

Tel +86 22 8371 4973
Fax +86 22 8371 2205
www.intertek.com.cn
www.intertek.com